



Ez Patch

100% Epoxy Floor Patching System

DESCRIPTION

Ez PATCH is a heavy duty high compression strength floor patch for repairing and resurfacing damaged plant floors - renews and repairs spalled & damaged floors, fills and eliminates damaged expansion joints, and anchors machinery.

FEATURES

- 100% Epoxy Resin Base with a Catalyst hardener and special blended aggregate
- 18,000 psi compression strength
- Will not break down at temperatures below 350° F
- Withstands heavy, abusive traffic
- Absorbs vibration and shock without cracking
- Excellent for expansion and contraction applications
- Highly resistant to acids, alkalis, solvents, heat and cold

HOW TO USE

1. Ready floor by removing all loose material. Sweep away dirt. Degrease areas which have a thick build-up of grease with BioClean 424.
2. Remove the cradle which contains Part B (pint) and 10 lbs. special aggregate.
3. Thoroughly mix Part A (which contains 12 lbs. special aggregate) until uniform.
4. Pour entire contents of Part (B) into Part (A), which is in the bottom of the pail. Mix Parts A & B for 2-3 minutes.
5. Add special aggregate from cradle to mixed Parts (A & B) to desired consistency, thick for troweling, thin for pouring.
5. Fill holes, cracks, crevices to level of existing floor. Feather edges with a trowel. Wet trowel with epoxy thinner and finish off to a smooth surface.

NOTE: You have 25-30 minutes to apply product to floor.

Ez PATCH dries in 12-18 hours for light traffic and 48-72 hours for heavy traffic.

Each kit covers 15-18 sq. ft. at 1/4" thickness

SPECIFICATIONS

	Part A	Part B	part C
Physical Form	viscous liquid	liquid	Granules
Color	clear to light amber	clear	gray
Odor	acrylate	amine	n/a
Specific Gravity	1.13	1.13	70 lbs/ft
Flash Point	200°+ F	200°+ F	None

HMIS SYMBOL

Health	2	3	1
Flammability	1	1	0
Reactivity	0	1	0

The logical choice for maintenance solution

P.O. Box 82501 i Rochester, MI 48308 i 248-941-0347 i Fax 248-941-0347